

## TRIPLEX BR QUALITY

### TECHNICAL SPECIFICATIONS

Basis Weight	Thickness	Stiffness Taber 15°	
		MD (gramf x cm) (c)	CD (gramf x cm) (c)
g/m <sup>2</sup> (a)	μm (b)		
280	340	88	31
300	360	107	37
320	380	134	48
350	425	174	64
375	457	208	79
385	470	221	84
400	485	241	93
420	507	276	107
450	540	328	129
500	620	414	164
550	685	480	192
600	750	545	220

<b>Humidity (%)</b>	6-8
<b>Brightness ISO (Elrepho) (%)</b>	Top 80 ± 2
	Back 66-72
<b>Cobb Test 1'</b>	Top Side 35-65
<b>Bulk</b>	1.23 cm <sup>3</sup> /g (d)
<b>Delamination (ft*lb*10<sup>-3</sup>)</b>	MD >= 50 CD >= 50
<b>Gloss</b>	40-55

<b>*Tolerances</b>	a (±3%)
	b (-5%)
	c (-15%)
	d (±5%)

#### Storage conditions:

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

#### The product is suitable for dry foodstuff packaging

The company reserves the right to change the technical specifications of its products