

## TRIPLEX R-KRAFT QUALITY

### TECHNICAL SPECIFICATIONS

Basis Weight	Thickness	Stiffness Taber 15°	
		MD (gramf x cm) (c)	CD (gramf x cm) (c)
g/m <sup>2</sup> (a)	μm (b)		
280	340	100	36
290	345	115	42
300	350	130	45
350	425	205	75
385	470	274	101
400	485	297	111
440	541	374	145
450	555	393	154
470	581	431	169
500	620	489	192
550	700	565	227

<b>Humidity (%)</b>	6-8
<b>Brightness ISO (Elrepho) (%)</b>	Top 80 ± 2
<b>Cobb Test 1'</b>	Top Side 35-65
<b>Bulk</b>	1.23 cm <sup>3</sup> /g (d)
<b>Delamination (ft*lb*10<sup>-3</sup>)</b>	MD >= 50 CD >= 50
<b>Gloss</b>	40-55

<b>*Tolerances</b>	a (±3%)
	b (-5%)
	c (-15%)
	d (±5%)

#### Storage conditions:

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

#### The product is suitable for dry foodstuff packaging

The company reserves the right to change the technical specifications of its products