







TRIPLEX RKR QUALITY

DESCRIPTION & STRUCTURE ANALYSIS

Fully Coated WLC
with kraft back

	Multiple Pigment Coating
	Unprinted PIW
	Printed PIW
	Mechanical Pulp
	PCW
	Unprinted PIW

TECHNICAL SPECIFICATIONS

Basis Weight	Thickness	Stiffness Taber 15°	
		MD (gramf x cm) (c)	CD (gramf x cm) (c)
g/m ² (a)	μm (b)		
320	380	160	57
350	425	205	75
400	485	297	111
450	555	393	154
500	620	489	192
550	700	565	227

Humidity (%)	6-8
Brightness ISO (Elrepho) (%)	Top 80 ± 2
Cobb Test 1'	Top Side 35-65
Bulk	1.23 cm ³ /g (d)
Delamination (ft*lb*10⁻³)	MD >= 50 CD >= 50
Gloss	40-55

*Tolerances	a (±3%)
	b (-5%)
	c (-15%)
	d (±5%)

Storage conditions

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

The product is suitable for dry foodstuff packaging

The company reserves the right to change the technical specifications of its products